

TEST REPORT

Number : HGHT05752023
报告号:

Date : Oct 12, 2018
日期: 2018年10月12日

申请公司 Applicant :	浙江绿树毛纺织有限公司 ZHEJIANG GREEN TREE WOOLEN TEXTILE		联系人 Attn :	张美华 Miss Zhang
地址 Address :	浙江省桐乡市濮院镇永越大道380号 NO. 380YONGYUE ROAD PUYUAN TOWNTONGXIANG CITY ZHEJIANG		来样时间 Date Received:	2018-10-10 Oct 10, 2018
样品描述 Sample Description :	成分: 55%尼龙 30% 粘纤 10% 兔毛 5% 羊毛 Fiber Composition :55% Nylon 30% Viscose 10% Rabbit Hair 5% Wool			
	颜色 Color	F09 东方红 F09 East Red	数量 Quantity	1个 One Piece
	款号 Style	-	订单号 P.O.No	-
	买家 Buyer's Name	-	SKU	-
	生产商名称: - Manufacture's Name			
	受检样品:客户认定为了一块针织面料。 Sample Description: One Piece Of Submitted Knitted Fabric .			
	检验类别: 委托检验 (送样检验) Test Type" Commission Test (Submitted Test)			
水洗标签符号 Care Instruction	-			
判定依据 Document Accordance	GB 18401-2010 国家纺织品基本安全技术规范, B类 GB 18401-2010 National General Safety Technical Code For Textile Products, Type B FZ/T 73005-2012 低含毛混纺及仿毛针织品 一等品 FZ/T 73005-2012 Low Wool Content And Wool Like Knitted Goods Class One			
检验项目 Test Performed	根据申请者的请求 Selected Test(s) As Requested By Applicant.			
备注 Remark	24支双股 -1803 批			

批准
Approved by

赵明

审核
Checked by

侯连连



TEST REPORT

Number : HGHT05752023
报告号:

Conclusion:
结论

Fibre Analysis(纤维成分定性分析/定量分析)	#
Formaldehyde Content(甲醛含量)	M
pH Value(pH 值)	F
Presence Of Odor(异味测试)	M
Colour Fastness To Rubbing(耐摩擦色牢度)	M
Colour Fastness To Perspiration(耐汗渍色牢度)	M
Colour Fastness To Water(耐水色牢度)	M
Colour Fastness To Washing(耐洗色牢度)	M

<u>Tested Sample</u> 测试样品	<u>Standard</u> 检测标准	<u>Result</u> 检测结果
Tested Sample 测试样品	GB 18401-2010 National General Safety Technical Code For Textile Products On Banned Azo Colourants GB 18401-2010 国家纺织产品基本安全技术规范附录 c 中关于禁用某些致癌芳香胺的规定	Pass 符合要求


Note : M = Meet Document Accordance
备注: M = 符合判定依据
= No Specified Requirement
= 没有指定要求
N/A = Not Applicable
N/A = 不适用

F = Below Document Accordance
F = 低于判定依据
* = No Submitted Information
* = 没有提供信息

Remark: The Chinese Version Of This Test Report Is The Standard One, The English Version Is Only For Reference. The Report Is Valid With Commission Test Only For The Samples In The Case Of Delivering Samples By Clients.

备注: 此报告以中文为主, 英文仅作参考。委托检验仅对来样负责。

批准
Approved by



审核
Checked by





TEST REPORT

Number : HGHT05752023
报告号:

Tests Conducted (As Requested By The Applicant)

测试内容 (以下测试依据申请人要求进行)

- 1 Fibre Analysis (FZ/T 01057.1~4-2007, GB/T 2910.2-2009, GB/T 16988-2013):
纤维成分定性分析/定量分析(FZ/T 01057.1~4-2007, GB/T 2910.2-2009, GB/T 16988-2013):

Marked
备注

=====

Based On Moisture Regain Weight
根据公定回潮率重量

53.4% 尼龙	55%尼龙
29.9% 粘纤	30% 粘纤
11.5% 兔毛*	10% 兔毛
5.2% 羊毛*	5% 羊毛
	55% Nylon
53.4% Nylon	30% Viscose 10%
29.9% Viscose	Rabbit Hair
11.5% Rabbit Hair*	5% Wool
5.2% Wool*	

Remark: *By Microscopical Analysis Procedure

备注: *通过显微镜分析方法

Moisture Regain Of Nylon 4.5%, Viscose 13.0%, Rabbit Hair 15.0% & Wool 15.0%
回潮率 尼龙 4.5%, 粘纤 13.0%, 兔毛 15.0%, 羊毛 15.0%

- 2 Formaldehyde Content (GB/T 2912.1-2009):
甲醛含量 (GB/T 2912.1-2009):

Requirement
要求

=====

Not Detectable
未检出

≤ 75 mg/kg

Remark: Detection Limit = 20 mg/kg
备注: 检出限 = 20 mg/kg



TEST REPORT

Number : HGHT05752023
报告号:

Tests Conducted (As Requested By The Applicant)
测试内容 (以下测试依据申请人要求进行)

3 pH Value (GB/T 7573-2009, KCL):
pH 值 (GB/T 7573-2009, KCL):

3.7

Requirement
要求
=====
4.0~8.5

4 Presence Of Odor (GB 18401-2010 Section 6.7):
异味测试 (GB 18401-2010, 6.7):

Odorless
无异味

Requirement
要求
=====
Odorless
无异味

5 Colour Fastness To Rubbing As Received (GB/T 3920-2008):
耐摩擦色牢度 (GB/T 3920-2008):

Dry
干
Wet
湿

4-5
4

Requirement
要求
=====
Class 1
一等品
≥ 3
≥ 2-3

Remark : Unit : Grade
备注: 单位: 级



TEST REPORT

Number : HGHT05752023
报告号:

Tests Conducted (As Requested By The Applicant)

测试内容 (以下测试依据申请人要求进行)

- 6 Colour Fastness To Perspiration (GB/T 3922-2013):
耐汗渍色牢度 (GB/T 3922-2013)

	Acid <u>酸</u>	Alkaline <u>碱</u>	Requirement 要求 =====
Colour Change 颜色变化	4-5	4-5	≥ 3-4
Colour Staining 沾色			≥ 3
-Nylon 锦纶	4	4	
-Viscose 粘纤	4-5	3-4	

Remark : Unit : Grade

备注: 单位: 级

TEST REPORT



中国认可
国际互认
检测
TESTING
CNAS L3439

Number : HGHT05752023
报告号:

Tests Conducted (As Requested By The Applicant)
测试内容 (以下测试依据申请人要求进行)

7 Colour Fastness To Water (GB/T 5713-2013):
耐水色牢度 (GB/T 5713-2013)

		Requirement 要求
		=====
		Class 1 一等品
Colour Change 颜色变化	4-5	≥ 3-4
Colour Staining 沾色		≥ 3
-Nylon 锦纶	4	
-Viscose 粘纤	4-5	

Remark : Unit : Grade
备注: 单位: 级

TEST REPORT

Number : HGHT05752023
报告号:

Tests Conducted (As Requested By The Applicant)

测试内容 (以下测试依据申请人要求进行)

8 Detection Of Amines In Dyestuff:
可分解致癌芳香胺染料测试

As Per GB18401-2010, GB/T17592-2011 And GB/T23344-2009 Was Used, Detected By Gas Chromatographic - Mass Spectrometric (GC-MS) Or High Performance Liquid Chromatographic Analysis.

根据 GB18401-2010 的要求, 采用测试方法: GB/T17592-2011 和 GB/T23344-2009, 气相色谱 / 质谱 (GC/MS) 联用仪或高效液相色谱 (HPLC) 检测。

	<u>Forbidden</u> 禁用芳香胺	<u>Cas No.</u>	<u>Result</u> 结果
1.	4-Aminodiphenyl 4-氨基联苯	92-67-1	N
2.	Benzidine 联苯胺	92-87-5	N
3.	4-Chloro-o-Toluidine 4-氯邻甲苯胺	95-69-2	N
4.	2-Naphthylamine 2-萘胺	91-59-8	N
5.	o-Aminoazotoluene 邻氨基偶氮甲苯	97-56-3	N
6.	2-Amino-4-Nitrotoluene 2-氨基-4-硝基甲苯	99-55-8	N
7.	p-Chloroaniline 对氯苯胺	106-47-8	N
8.	2,4-Diaminoanisole 2,4-二氨基苯甲醚	615-05-4	N
9.	4,4'-Diaminodiphenylmethane 4,4'-二氨基二苯甲烷	101-77-9	N
10.	3,3'-Dichlorobenzidine 3,3'-二氯联苯胺	91-94-1	N
11.	3,3'-Dimethoxybenzidine 3,3'-二甲氧基联苯胺	119-90-4	N
12.	3,3'-Dimethylbenzidine 3,3'-二甲基联苯胺	119-93-7	N
13.	3,3'-Dimethyl-4,4'diaminodiphenylmethane 3,3'-二甲基-4,4'-二氨基二苯甲烷	838-88-0	N

TEST REPORT

Number : HGHT05752023
报告号:

Tests Conducted (As Requested By The Applicant)

测试内容 (以下测试依据申请人要求进行)

Detection Of Amines In Dyestuff (CONT'D)

可分解致癌芳香胺染料测试

14.	p-Cresidine 2-甲氧基-5-甲基苯胺	120-71-8	N
15.	4,4'-Methylene-Bis(2-Chloroaniline) 4,4'-亚甲基-二-(2-氯苯胺)	101-14-4	N
16.	4,4'-Oxydianiline 4,4'-二氨基二苯醚	101-80-4	N
17.	4,4'-Thiodianiline 4,4'-二氨基二苯硫醚	139-65-1	N
18.	o-Toluidine 邻甲苯胺	95-53-4	N
19.	2,4-Toluylenediamine 2,4-二氨基甲苯	95-80-7	N
20.	2,4,5-Trimethylaniline 2,4,5-三甲基苯胺	137-17-7	N
21.	o-Anisidine 邻氨基苯甲醚	90-04-0	N
22.	4-Aminoazobenzene 4-氨基偶氮苯	60-09-3	N
23.	2,4-Xylidine 2,4-二甲基苯胺	95-68-1	N
24.	2,6-Xylidine 2,6-二甲基苯胺	87-62-7	N

Remark : N = Not detected/未检出

Detection Limit/检出限 = 5 mg/kg

Requirement/技术要求 = 20 mg/kg (Max.最大值)

TEST REPORT

Number : HGHT05752023
报告号:

Tests Conducted (As Requested By The Applicant)

测试内容 (以下测试依据申请人要求进行)

- 9 Colour Fastness To Washing (GB/T 12490 A1S-2007, Single Test, 30 Minutes Mechanical Wash At 40°C In 0.4% ECE Reference Detergent With 10 Steel Balls):
耐洗色牢度 (GB/T 12490 A1S-2007, 独立测试, 40°C, 30 分钟机械洗涤, 用浓度 0.4%ECE 合成洗涤剂 and 10 个钢珠):

		Requirement 要求 =====
		Class 1 一等品
Colour Change 颜色变化	4-5	≥ 3-4
Colour Staining 沾色		≥ 3
-Nylon 锦纶	4-5	
-Viscose 粘纤	4-5	

Remark : Unit : Grade
备注: 单位: 级

End of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

This report shall not be reproduced except in full, without written approval of the laboratory.

本报告仅基于申请人的指示及/或申请人提供的信息和材料而作出, 不应视为采取任何行动的建议。关于本报告, Intertek 不对客户以外的任何人负有谨慎责任或其他责任, Intertek 对客户也只在向其申请人提供服务的条件条款有明确规定的范围承担责任。Intertek 不就本报告作出除前述条件条款范围之外的任何明示或隐含形式的担保或陈述。Intertek 致力于在勤勉细致的基础上进行审核, 不对因本报告引起的或与本报告有关的任何损失承担任何责任, 包括合同、侵权、法规或其它责任, 除非诉讼结果显示为因 Intertek 严重疏忽或故意的不当行为而造成。

未经本实验室书面批准, 不得复制本检测报告 (全文复制除外)。